



ARDEX WPM 155

(Undertile PU Acrylic Hybrid Membrane)

Modified Polyurethane Waterproof Membrane

Can be tiled over - excellent adhesion with ARDEX tile adhesives

Environmentally friendly - solvent free, suitable for confined areas

Class III Membrane - as per AS/NZS4858 Wet Area Membranes

ARDEX Australia Pty Ltd
20 Powers Road
Seven Hills NSW 2147
Tel: (02) 9851 9199
Fax: (02) 9674 5621
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX New Zealand Ltd
32 Lane St, Woolston
Christchurch, New Zealand
Tel: (03) 384 3029
Fax: (03) 384 9779
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX WPM 155

(Undertile PU Acrylic Hybrid Membrane)

DESCRIPTION

Water-based polyurethane-acrylic waterproofing membrane developed for high performance under-tile waterproofing.

- Tough flexible film
- UV stable when left exposed (non trafficable)
- Long shelf life
- Meets Green Building Council of Australia Greenstar requirements IEQ-13, IEQ-11
- Can be tiled over – good adhesion with ARDEX tile adhesives
- Excellent adhesion to a wide range of substrates
- Fast drying
- Class III Membrane, as per AS/NZS 4858 Wet Area Membranes

RANGE OF APPLICATIONS

For commercial and residential internal/external wet areas, balconies, decks and other areas that will be tiled or otherwise protected from regular foot traffic. Not suitable for permanent immersed conditions. For conditions of permanent immersion, it is recommended that Ardex WPM 002 (Superflex Two Part) is used. For further information please call ARDEX Technical Services.

SUBSTRATES

Concrete

Cured for minimum 28 days, wet concrete should be allowed to dry thoroughly or sealed with one coat of ARDEX WPM 300 at coverage rate of 3.0m² per litre.

Renderers and Screeds

Cured for min 7 days. Wet render should be allowed to dry thoroughly or sealed with one coat of WPM 300 at coverage rate of 3.0m² per litre and allowed to cure overnight.

Fibre cement sheets

Wet area grades only.

Plasterboard

Wet area grades only.

Plywood

Structural plywood (PAA branded) or marine grade.

PRIMERS

ARDEX WPM 155 is suitable to use over ARDEX WPM 300, or WPM 270 or WPM 265 or ARDEX Multiprime.

APPLICATION

ARDEX WPM 155 should be thoroughly mixed to a uniform mix and ensure the coating is applied evenly at recommended coverage rates. Mobile joints should be reinforced using Deckweb and the

membrane must be lapped to intrusions such as waste outlets in accordance with AS 3740. Apply ARDEX WPM 155 by brush or roller. A medium nap (8-12mm pile) or 50mm long bristle paint brush is recommended.

COVERAGE

This will vary with the porosity of the substrates. Two coats are recommended to get optimum performance.

For floors

A dry film thickness of 1.0mm is required. A 20kg unit (15 Litres) will cover approximately 8.6m² (based on two coats).

For walls

A dry film thickness of 0.5mm is required. A 20kg unit (15 Litres) will cover approximately 17.2m².

DRYING TIME

Recoat time is 1-2 hours in between first and second coats. Drying time on flat surfaces under standard conditions is 4 hours. However, dry through time will be slowest in areas where ARDEX WPM 155 is applied over silicone bond breaker, or is reinforced. Make sure these areas are dry before tiling. In some cases, this can vary from 24 hours to 48 hours.

Full cure of the product is 3 days after application at 23°C. Drying times will vary depending on humidity, surface temperature and porosity of substrates.

PACKAGING

20kg (approximately 15 litres).

SHELF LIFE

12 months when stored in the original unopened packaging in a dry place at 23°C.

CLEANING

Wash hands, brushes, rollers with water while product is still fresh. For cured material, use mineral turpentine.

PRECAUTIONS

All surfaces must be structurally sound, dry and free from all surface contaminants.

Do not use ARDEX WPM 155 under the following conditions:

- Areas subject to negative hydrostatic pressure or rising damp.
- Wet substrates or green screeds/concrete – need to be sealed with one coat ARDEX WPM 300 as described earlier.
- Surface temperatures below 10°C or greater than 35°C.

SAFETY DATA

ARDEX WPM 155 is a non-hazardous and non-dangerous product. Wear protective clothing when handling. Wash off splashes with clean water. In case of eye contamination, rinse thoroughly with clean water. If irritation persists, seek medical advice.

Additional information is listed in the Material Safety Data Sheet.

QUALITY PRODUCT

ARDEX WPM 155 is manufactured and tested to ARDEX procedures which are maintained in accordance with Quality System Standard ISO 9001.

TECHNICAL DATA

Properties of Liquid Material

Appearance	Blue/Grey
Viscosity (6/20/25°C) AS 1580:1990	30,000 cps
Density (kg/L) AS 4459:1999	1.36
Solids, by mass AS 1580:1992	66-69%
Volume solids AS 1580	57%

Properties of the Cured Membrane

Tensile Strength, MPa AS 1145	1.2 MPa
% Elongation	>350%
Shore A Hardness	65-75

Water Vapor Transmission 1.2g/24hrs.m²
(AS4858/ASTME96)

ARDEX Australia Pty Ltd

NSW Ph (02) 9851 9100 Fax (02) 9838 7970
QLD Ph (07) 3817 6000 Fax (07) 3881 3188
VIC/TAS Ph (03) 9308 9255 Fax (03) 9308 9332
SA Ph (08) 8268 2511 Fax (08) 8345 3207
WA Ph (08) 9256 8600 Fax (08) 9455 1227

ARDEX New Zealand Ltd

Christchurch Ph (03) 3843 029 Fax (03) 3849 779
Auckland Ph (09) 2967 690 Fax (09) 2967 689
Wellington Ph (04) 5685 949 Fax (04) 5686 376

Technical Services Toll Free: 1800 224 070

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.