



## technical data sheet

# BOSCOSEAL AC2

## 1 Part Fibre Reinforced Waterproofing Membrane

### PRODUCT

Boscoseal AC2 is a 1 part water based acrylic polymer, fibre reinforced, waterproofing membrane.

### DESCRIPTION

Boscoseal AC2 is specifically formulated for commercial and residential internal and external waterproofing applications. Low in odour, it is well suited to internal use and offers excellent, easy application by brush or roller. The fibre, reinforced composition of Boscoseal AC2 combines a matrix binder within the membrane structure to provide extra strength and add high build dry film thickness. Boscoseal AC2 does not require the use of additional reinforcing matting.

### RECOMMENDED USES

- Internal wet areas to be tiled including showers, bathrooms, toilets and laundries.
- External Balconies and decks prior to the installation of a covering material such as tiles or non-solvent topping systems.
- Non traffic podium or roof areas subjected to weather and U.V. exposure.
- Suitable for waterproofing a broad range of substrates including: concrete, cement render, brickwork, particleboard, plywood, plasterboard, gyprock, composition board and fibre cement sheeting.
- Planter boxes and tubs.

### FEATURES & BENEFITS

- Low odour for ease of use in internal applications.
- Excellent rolling and brushing ability.
- 10Year material guarantee.
- Australian made.
- Environmentally friendly.
- Fibre reinforced, does not require the use of additional reinforcing matting.
- Water based for easy application and clean up.
- Flexible.
- Excellent UV light resistance.

### COVERAGE

Coverage rates are dependent on substrate composition, porosity and condition.

Boscoseal AC2 should be applied as a 2 coat system.

Each coat should be applied at 0.8mm wet film thickness, which will cure to a 0.6mm dry film thickness.

Application of two coats at this coverage rate will provide the minimum 1.2mm dry film thickness required to ensure an effective, waterproofing membrane.

### PERFORMANCE PROPERTIES

(Do not use for specification purposes)

Colour	White
Drying time	24 hours between coats @ 25°C and 50% RH
Elongation	250% Approx
Tensile Strength	1.9N/mm <sup>2</sup>
Cure before tiling	Minimum 3 days @ 25°C and 50% RH
Application Temp	+10°C to +35°C
Flammability	Non-flammable

### PACKAGING

Boscoseal AC2 is supplied in 15 litre plastic pails.

### APPLICATION - IMPORTANT NOTES

It is recommended that the installation of Bostik Boscoseal AC2 be carried out by professional applicators of waterproofing membranes. Installation is to be strictly in accordance with the manufacturer's written instructions. The Bostik Technical Division must approve any modification or variances to these specifications in writing. Read the following notes in conjunction with precautions;

- The application of Boscoseal AC2 must comply with AS3740-1994 "Waterproofing of Internal Wet Areas in Residential Buildings".
- Commencement of membrane application shall be taken as acceptance of the substrate suitability and preparation by the applicator.
- Ensure necessary primers have been allowed to dry for the minimum recommended period prior to the application of Boscoseal AC2.
- Ensure sufficient Boscoseal AC2 is applied in two coats to achieve a total 1.2mm thick dried film.
- Ensure recoat times are adhered to between applications. A minimum of 24 hours (refer to performance properties) is required between coats, overnight preferably if temperatures are below +20°C.
- When applying final coat, ensure no imperfections are present in the membrane.
- Boscoseal AC2 must be allowed to fully cure before tiling

### PREPARATION & APPLICATION PROCEDURE:

#### 1. PRIMING

- All surfaces will require priming.
- Porous surfaces must be primed with Bostik AC Primer. Allow AC Primer to dry approximately 30 minutes prior to application of Boscoseal AC2.
- Very 'boney' or porous concrete may require more than one coat of AC primer to fill and penetrate the pores of the concrete.

- Non porous surfaces such as existing tiles and burnished concrete will require priming with Bostik Ultra NP Primer.
- Metal surfaces and PVC pipes should be primed with Bostik 5077 primer.
- All designated primers must be applied in accordance with the current applicable primer technical data sheet.
- For pre-treated or suspect surfaces, contact Bostik technical service.

## 2. SUBSTRATE

- **All surfaces must be primed.**
- Before the application of Boscoseal AC2 all surfaces must be clean, dry and structurally sound. The substrate must be free of voids, curing compounds, sharp objects, laitance, loose material, oils, grease or sealers.
- New concrete must be cured for 28 days, mortar beds and cement render cured for 7 days.
- Do not apply over concrete slabs containing high moisture content (above 15%).
- Holes, non-structural cracks over 5mm and other particularly rough surfaces should be repaired using a recommended Bostik floor levelling compound or Bostik Ultrarapid Set polymer repair mortar.
- Very 'boney' or porous concrete must be primed or moisture sealed prior to any application (see priming).
- All cement sheet joints and movement joints designed in base substrates where Boscoseal AC Primer or AC Membranes will be in direct contact must be sealed with Bostik neutral cure silicone or Simson SMP joint sealants prior to membrane application. Sealants must not be applied in, or to, moist or damp surfaces
- Fibrous cement sheeting and plasterboard must be installed in accordance with manufacturer's directions.

## 3. MOISTURE/VAPOUR BARRIER

- Boscoseal AC2 must **not** be applied to surfaces that are moist or damp. Applications to these surfaces can result in adhesion failure and surface bubbling of the membrane.
- Applications requiring access onto moist, 'green' or uncured concrete will first require the application of Bostik Moisture Seal epoxy vapour barrier which will act as a curing compound and moisture transmission barrier.
- Bostik Moisture Seal must be applied in a two-coat system as per Technical Data Sheet. Boscoseal AC2 must be applied immediately the second coat 'tacks off'.
- If Boscoseal AC2 cannot be applied within 24 hours of the second coat of Moisture Seal curing, a third coat must be applied

## 4. CRACKS & NARROW JOINT SEALING

- All cracks must be cleaned with loose material removed.
- For cracks and joints up to 5mm apply a bead of Bostik Neutral Cure Silicone into the crack and extending 5mm either side. Tool smooth with spatula.
- Once silicone is tack free prime the repair area with Bostik AC Primer to a width of 150mm each side of repair.
- Allow AC Primer to dry approximately 30 minutes.
- Apply two coats of Boscoseal AC2 over the primed area achieving a minimum dry film thickness of 1.2mm.
- Cracks over 5mm must be repaired and designed movement joints sealed as detailed in substrate preparation section.

## 5. INTERNAL WET AREAS – SEALING CORNERS & WASTE OUTLETS

- **Do not** use polyurethane based sealants in these applications.
- Ensure falls required in the screed to shower recess base, pipe outlets, angles and drainage is installed correctly.
- All corners and substrate gaps around taps, shower outlets, waste outlets, pipes, drains, flashings and nail/screw holes must be sealed using Bostik Neutral Cure Silicone or Simson SMP sealants.
- Apply a 10mm bead of sealant by caulking gun directly into all wall/floor, hob/floor, hob/wall and wall/wall corners to intending tile height.
- Sealant should be spatula tooled smooth around fittings and pressed into corners creating a triangular fillet.
- Allow sealant to tack off (approximately 30 minutes).
- Apply primers after sealant tack off, to all areas intended for Boscoseal AC2 application.

## 6. SHOWER MEMBRANE APPLICATIONS

Primer applications must be dry.

### ➤ Walls

- Apply Boscoseal AC2 to the internal wall corners extending out 100mm onto each wall of the shower using a paintbrush. Ensure all corners are well coated. This must extend past the height of the shower rose. It is important to coat around any tap body protrusions through the wet area wall as per AS3740.
- The wall/floor junctions must then be coated extending 100mm onto the floor and up the wall 100mm.
- Where the height of the hob is greater than 75mm, then the Boscoseal AC2 must extend at least 25mm above the height of the hob.
- Apply Boscoseal AC2 to wall surfaces coating above anticipated shower rose height, covering all previously coated wall/wall junctions, wall/floor junctions, and tap protrusion surrounds.

### ➤ Shower base

- The shower base is to be fully coated. Boscoseal AC2 must be dressed down into the waste at least 50mm.
- Once the initial coating is dry, recoat the entire area to be waterproofed, including full cover over the initial coating.

## 7. WET AREA FLOOR & EXTERNAL DECKS APPLICATIONS

Primer applications must be dry

- If the wet area floor, balcony or deck areas to be coated are subject to service or other building penetrations, it is recommended, if possible, to install a flanged metal up stand around the penetration.
- Prime metal up stand with Bostik 5077 primer and seal off the perimeter of the penetration with a 10mm bead of Bostik Neutral Cure Silicone.
- Apply Boscoseal AC2 into wastes, drains or onto puddle flanges. Boscoseal AC2 must be dressed down into the waste at least 50mm.
- Apply an initial coat of Boscoseal AC2 either side of all wall/floor junctions and sheet flooring joints. Extend the coating at least 100mm either side of the joins.
- Once the initial coating is dry, recoat the entire floor area to be waterproofed, including over the initial coating.

## 8. ROOF APPLICATIONS

Boscoseal AC2 is recommended as a waterproof membrane for non-traffic areas. (Application method is the same as for wet area floors/decks).

These areas of application should not be accessed until membrane has fully cured.

## TILING AND MORTAR BED COVERING

To eliminate possible surface contamination or damage, it is recommended tiling, mortar bed applications or finished flooring installations be carried out it as soon as possible after full cure of the membrane. These installations may be carried out after the Boscoseal AC2, two-coat system, has been allowed to cure for a minimum of 3 days at a temperature of 25°C (slightly longer in lower temperatures).

Movement joints provided in tiling should be filled with either Bostik Seal 'N' Flex 1 or FC polyurethane sealant or Bostik neutral cure anti-fungal silicone sealant.

## TILE ADHESIVE

Proprietary commercially available tile adhesives may be used such as Architectural & Structural Adhesives (ASA); ASAFLEX, CONFLEX, MEGAFIX or FIXALL mixed with MEGALASTIC and/or equal, recommended and applied in strict compliance with manufacturer's instructions.

## PRECAUTIONS

- Do not apply where the surface temperature is below +10°C or greater than 35°C.
- Boscoseal AC2 is not a vapour barrier nor designed to stop a hydrostatic head of water pressure. (For this application, Bostik Moisture Seal should be used).
- Do not apply on wet, contaminated, or friable substrates.
- Do not apply externally if raining or rain is imminent.
- Do not apply to surfaces with protective coatings without prior consultation with Bostik.
- The rate of cure will be dramatically reduced when air or substrate temperatures are below +10°C or if applied over a vapour barrier or untreated concrete.
- The application rate of Boscoseal AC2 should not be extended over the recommended coverage of 1 litre per square metre or under 0.8mm wet film thickness in one application.
- A third coat of Boscoseal AC2 may be necessary if imperfections in the cured membrane are present.
- Do not dilute with water or extend with cementitious powders or other additives.
- Boscoseal AC2 requires atmospheric conditions to cure. It should not be used in totally confined or air free spaces.
- Boscoseal AC2 is not trafficable and should not be used as a wearing surface for foot or vehicle traffic.
- Do not apply over treated pine.
- Totally impervious substrates such as epoxies and rigid fibreglass will require priming.

- Due to low flexibility, Boscoseal AC2 is not recommended for planter boxes or areas where high movement is anticipated.
- Boscoseal AC2 will not span gaps and should only be applied to continuous surfaces.
- Boscoseal AC water based membranes must not come in direct contact with polyurethane sealants in any application.
- Any intended use of Boscoseal AC2 outside of specified use should be referred to Bostik technical services for approval.

## P.A.T.S PROGRAMME (Pretested Adhesion To Substrate)

Bostik offer a service in which a program has been established to eliminate potential field problems by pre-testing Bostik coatings and membranes with samples of building materials to which the systems will be applied. This service is available on large projects where pre-application testing will aid in determining the proper surface preparation method to achieve optimum adhesion. Consult a Bostik representative for further information.

## HEALTH AND SAFETY

- If swallowed, do not induce vomiting. Give a glass of water; contact a doctor or Poisons Information Centre.
- For more detailed information refer to Material Safety Data Sheet.

## CLEAN-UP

Boscoseal AC2 can be cleaned from skin and application equipment with water while the membrane is still wet.

## STORAGE

Store in original sealed container under cover in dry conditions. Boscoseal AC2 has a shelf life of 12 months in original unopened container if stored between 5°C and 35°C. Do not freeze.

Item No	Product	Size
301248	Boscoseal AC 1	White 15 litre
301256	Boscoseal AC 2	White 15 litre
298476	Boscoseal AC 3	Grey (2 part kit)
300217	AC Primer	20 Litre White
263362	Moisture Seal	8 Litre Grey
263370	Moisture Seal	20 Litre Grey
227935	5077 Primer	1 Litre Clear
287032	Ultra NP Primer	4 Litre Green
272496	Ultrarapid Set	20 Kg Grey

*The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.*

**ALL SALES ARE EXPRESSLY LIMITED TO THE TERMS AND CONDITIONS OF SALE OF BOSTIK AUSTRALIA PTY LTD**



**BOSTIK**  
AUSTRALIA PTY LTD  
Phone: +61-3-9279 9333  
Fax: +61-3-9279 9240

**BOSTIK**  
NZ LIMITED  
Phone: +64-4-567 5119  
Fax: +64-4-567-5412

**BOSTIK**  
SINGAPORE PTE LTD  
Phone: +65-6863 4088  
Fax: +65-6863 4077

**BOSTIK**  
(MALAYSIA) SDN BHD  
Phone: +606 764 3246  
Fax: +606 764 3248

**SYDNEY**  
Phone: 02 8825 3488  
Fax: 02 8825 3411

**ADELAIDE**  
Phone: 08 8244 0511  
Fax: 08 8244 0522

**PERTH**  
Phone: 08 9258 6218  
Fax: 08 9258 7687

**BRISBANE**  
Phone: 07 3260 2206  
Fax: 07 3260 2123

**(ABN 79 003 893 838)**

Product:	Boscoseal AC2
Issue Date:	July 2004
Issue No:	1
Division:	Construction
Total Pages:	3