

## Renderoc HB70

**High build, high strength, very low shrinkage, patch repair mortar, compatible with concrete >45 MPa**

### USES

For the reinstatement of localised patch repairs and larger areas where suitable reinforcement is incorporated. Renderoc HB70 is alkaline in nature and will protect embedded steel reinforcement. It is specifically designed for locations where high build and high compressive strengths are required or in locations where good abrasion resistance is necessary. The mortar is suitable where resistance is required to chlorides and carbon dioxide.

**Important note 1:** Renderoc HB70 is approved for use with Norcure Realkalisation and Norcure Desalination. When using it in conjunction with these methods, the concrete bonding primer should be water or an OPC: water slurry. Polymer or epoxy bonding agents should not be used. No steel primer should be applied. Refer to your local Parchem sales office for advice.



**Important note 2:** Renderoc HB70 is suitable for use with the Fosroc Galvashield XP incipient anode protection, with a resistivity <math><15,000 \Omega \text{ cm}</math> @ 28 days.



### ADVANTAGES

- High strength and high abrasion resistance
- High build repairs
- Exceptional system of shrinkage compensation, provides long-term dimensional stability
- Low permeability provides sound protection against carbon dioxide and chlorides
- Can be applied by the wet or dry spray process for fast, exceptionally high build repairs with enhanced characteristics
- Suitable for internal and external use
- Pre-bagged to overcome site-batched variations - only the site-addition of clean water required
- Contains no chloride admixtures

### DESCRIPTION

Renderoc HB70 is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent, high strength repair mortar. The material is based on Portland cement, graded aggregates, special fillers and chemical additives and is polymer modified to provide a mortar with good handling characteristics, while minimising water demand. The hardened product exhibits excellent thermal compatibility with concrete and outstanding water repellent properties. The low water requirement ensures fast strength gain and long-term durability.

### DESIGN CRITERIA

Renderoc HB70 is designed for vertical or horizontal use. It can be applied up to 40 mm thickness in vertical sections. Greater thickness can be achieved in small pockets or by the use of formwork. In horizontal locations, Renderoc HB70 can be applied up to 150 mm thickness. Thicker sections can be built up in layers. The material should not be applied at less than 5 mm thickness. Thicknesses greater than those nominated in large areas can be achieved by spray application.

### PROPERTIES

The following results were obtained at a water:powder ratio of 0.14 and temperature of 20°C.

Test method	Typical result
<b>Compressive strength</b> (BS 6319 Pt 2: 1983 - dry cure):	20 MPa @ 1 day 70 MPa @ 28 days
<b>Flexural strength</b> (BS 6319 Pt 3: 1983):	10 MPa @ 28 days
<b>Coefficient of thermal expansion:</b>	7 - 12 x 10 <sup>-6</sup> /°C
<b>Setting time (BS 5075) –</b> Initial set: Final set:	3 hours, 15 minutes 4 hours, 30 minutes
<b>Fresh wet density:</b>	Approx. 2200 kg/m <sup>3</sup> dependent on actual consistency used

## TECHNICAL SUPPORT

Parchem offers a technical support service to specifiers, end-users and contractors, as well as on-site technical assistance.

## SPECIFICATION CLAUSE

### STEEL REINFORCEMENT PRIMER

The steel reinforcement primer shall be Nitoprime Zincrich, a single-component zinc-rich epoxy resin. The primer shall be an 'active' type, capable of avoiding the generation of incipient anodes in the immediately adjacent locations. It shall be fully compatible with the Renderoc system of concrete repair.

### REPAIR MORTAR

The polymer modified shrinkage-compensated reinstatement mortar shall be Renderoc HB70 a single-component cement-based blend of powders to which only the site-addition of clean water shall be permitted. The cured mortar shall achieve 70 MPa compressive strength and 10 MPa flexural strength at 28 days.

## APPLICATION INSTRUCTIONS

### PREPARATION

Saw cut or cut back the extremities of the repair locations to a minimum depth of at least 5 mm to avoid feathering and to provide a square edge. Break out the repair area to a minimum depth of 5 mm up to the sawn edge.

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae. Where breaking out is not required, roughen the surface and remove any laitance by light scabbling or grit-blasting.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test.

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Grit-blasting is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after grit-blasting to remove corrosion products from pits and imperfections within its surface.

### REINFORCING STEEL PRIMING

Apply one full coat of Nitoprime Zincrich and allow to dry before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made and, again, allowed to dry before continuing.

(If Galvashield XP are to be embedded into the Renderoc HB70 patch repair, refer to the current Galvashield XP Technical Data Sheet for priming instructions).

### SUBSTRATE PRIMING

The substrate should be thoroughly soaked with clean water and any excess removed prior to applying one coat of Nitobond HAR primer and scrubbing it well into the surface. Renderoc HB70 is to be applied as soon as the primer becomes tacky. If the Nitobond HAR dries prior to the application of the Renderoc HB70, then the Nitobond HAR is to be reprimed and the repair mortar applied when primer is tacky. If the Nitobond HAR is too wet, vertical build up of the Renderoc HB70 mortar may be difficult.

In exceptional circumstances, e.g. where a substrate/repair barrier is required or where the substrate is wet or likely to remain permanently damp, Nitobond EP bonding aid should be used. Contact your local Parchem sales office for further information.

### MIXING

Care should be taken to ensure that Renderoc HB70 is thoroughly mixed. A forced-action mixer is essential. Mixing in a suitably sized drum using an approved spiral paddle in a slow speed (400/500 rpm) heavy-duty drill is acceptable for the occasional one-bag mix. Free-fall mixers must not be used. Mixing of part bags should never be attempted.

For normal applications, place 2.8 - 3.0 litres of drinking quality water into the mixer and, with the machine in operation, add 1 full 20 kg bag of Renderoc HB70 and mix for 3 - 5 minutes until fully homogeneous. Note that powder must always be added to water. Dependent on the ambient temperature and the desired consistency, the amount of water required may vary slightly but should not exceed 3.0 litres / 20 kg bag of Renderoc HB70.

## APPLICATION

Exposed steel reinforcing bars should be firmly secured to avoid movement during the application process as this will affect mortar compaction, build and bond.

Apply the mixed Renderoc HB70 to the prepared substrate by gloved hand or trowel. Thoroughly compact the mortar on to the primed substrate and around the exposed reinforcement. Renderoc HB70 can be applied up to 40 mm thickness in vertical sections but greater thickness in smaller pockets or with the use of formwork. If formwork is used, it should have properly sealed faces to ensure that no water is absorbed from the repair material. In horizontal locations, Renderoc HB70 can be applied up to 150 mm thickness.

If sagging occurs during application to vertical surfaces, the Renderoc HB70 should be completely removed and reapplied at a reduced thickness on to the correctly reprimed substrate.

Note: the minimum applied thickness of Renderoc HB70 is 5 mm.

## SPRAY APPLICATION

Renderoc HB70 can be applied by the wet spray technique. In circumstances where large areas of repair are required, the rapid placement and higher build attainable by these methods offer economic advantages over hand-trowelling. The resultant repair also offers a generally more dense compound with greatly enhanced mortar/substrate bond characteristics. For further details on the wet and dry spray techniques, including selection of spraying machines and nozzles, consult Wet or Dry Spray Application Guides or your local Parchem sales office.

## FINISHING

Renderoc HB70 is finished by striking off with a straight edge and closing with a steel float. Wooden or plastic floats, or damp sponges may be used to achieve the desired surface texture. The completed surface should not be overworked.

## LOW TEMPERATURE WORKING

In cold conditions down to 5°C, the use of warm water (up to 30°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should then be adopted. The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

## HIGH TEMPERATURE WORKING

At ambient temperatures above 35°C, the material should not be used as this will cause premature setting.

## CURING

Renderoc HB70 is a cement-based repair mortar. In common with all cementitious materials, Renderoc HB70 must be cured immediately after finishing in accordance with good concrete practice. The use of Nitobond AR, sprayed on to the surface of the finished Renderoc in a continuous film, is recommended. Large areas should be cured as trowelling progresses (0.5 m<sup>2</sup> at a time) without waiting for completion of the entire area. In fast drying conditions, supplementary curing with polythene sheeting taped down at the edges must be used. In cold conditions, the finished repair must be protected from freezing.

## OVERCOATING WITH PROTECTIVE DECORATIVE FINISHES

Renderoc HB70 is extremely durable and will provide excellent protection to the embedded steel reinforcement within the repaired locations. The surrounding parts of the structure will generally benefit from the application of a protective barrier/decorative coating to limit the advance of chlorides and carbon dioxide, thus bringing them up to the same protective standard as the repair itself. Parchem recommend the use of the Dekguard or Emer-Clad range of protective, anti-carbonation coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment. Dekguard or Emer-Clad products may be applied over the repair area without prior removal of the Nitobond AR curing membrane. Other curing membranes must be removed prior to the application of Dekguard or Emer-Clad products.

## CLEANING

Nitobond AR and Renderoc HB70 should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Equipment used with Nitoprime Zincrich and Nitobond EP should be cleaned with Solvent 10.

## LIMITATIONS

Renderoc HB70 should not be used when the temperature is below 5°C and falling. Do not mix part bags. The product should not be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature or substrate conditions, consult your local Parchem office.

## ESTIMATING

### SUPPLY

<b>Renderoc HB70:</b>	20 kg bag
<b>Nitoprime Zincrich:</b>	1 litre can
<b>Nitobond AR:</b>	1, 5 and 20 litre container
<b>Nitobond HAR:</b>	1, 5 and 20 litre container
<b>Nitobond EP:</b>	1.5 and 6 litre pack
<b>Solvent 10:</b>	4 and 20 litre can

### COVERAGE AND YIELD

<b>Renderoc HB70:</b>	Approx. 10.2 litres / 20 kg bag (1.0 m <sup>2</sup> @ 10 mm thickness)
<b>Nitoprime Zincrich:</b>	7 m <sup>2</sup> / litre (approx.)
<b>Nitobond AR:</b>	6 - 8 m <sup>2</sup> /litre
<b>Nitobond EP:</b>	4 - 5 m <sup>2</sup> /litre

Notes: the actual yield per bag of Renderoc HB70 will depend on the consistency used. The yield will be reduced if the material is applied by a spray technique. The coverage figures for liquid products are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

## STORAGE

### SHELF LIFE

All products have a shelf life of 12 months if kept in a dry store in the original, unopened bags or packs.

### STORAGE CONDITIONS

Store in dry conditions in the original, unopened bags or packs. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to 4 - 6 months. Nitobond AR should be protected from frost.

## ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

## IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

## PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

\*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. \*Denotes a trade mark of Fosroc International Limited.